

Magic Discharge For Garment

FOR KNITTED FABRIC / GARMENTS

COLOURED/ NATURAL FABRIC COLOUR DISCHARGE

Magic Colour Discharge 600

WHITE DISCHARGE

Magic White Discharge 200

RECEIPE :-

	WHITE DISCHARGE	NATURAL DISCHARGE	WHITE DISCHARGE	COLOUR DISCHARGE
Magic White Discharge 200	98	--	--	--
Magic Colour Discharge 600	--	98	98	94
Laser Pigment Emulsions	--	--	--	04
Magic White 2121	--	--	10	--
FIXER MAGIC WB	02	02	02	02
	100	100	100	100

PRINT → DRY → CURED

FUSING 170°C - 180°C → 10-15 SEC

CONVEYER 170°C → 1 TO 2 MINTS

Precaution:

- Semi dried, discharge printed fabric should not be stacked on each other or piled to get contamination of discharge paste on un-printed portion.
- Check dischargibility of fabric before bulk printing
- Drying of discharge print varies as per quantity of Ink Transferred on Fabric
- After curing & Fusing of discharge prints, Garments should be cooled down & then filed / stacked to prevent mark off effect of for improved stretch-ability.
- **If necessary Add water to drop Viscosity to Penetrate to give backside Penetrations**

Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility.

It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

Electron Group
230 New Apollo Estate, Mogra Lane, Andheri (E), Mumbai 400069, India. Ph- +91 99200 77766
e-mail- info@electrongroup.com, website- <http://www.electrongroup.com>

Copyright © 2025 Electron Group