



Textile  
Printing

## STRETCH WHITE KBX/ECO

### (GOTS Approved Stretchable, High Opaque Printing Ink for Rotary Machine)

- **"STRETCH WHITE KBX/ECO"** High Opaque White Ink for printing stretchable motifs on Dark Dyed Knitted Hosiery Specifically Alphabets which can't printed Two Times.
- **"STRETCH WHITE KBX/ECO"** is specially designed to get maximum white print motifs at Minimum time of contact on the Rotary Printing Machine.
- **"STRETCH WHITE KBX/ECO"** is suitable for Hosiery and Knitted as well as woven fabric.
- **"STRETCH WHITE KBX/ECO"** is suitable for 100 % Cotton, Polyester and their blends on Knitted Fabric with comparatively better opacity and stretch ability.

### Value Addition :

- **"STRETCH WHITE KBX/ECO"** can be made highly stretchable ,after addition of Binder Laser 5050 to get more Stretch ability desired for hosiery and knitted garments.
- **"STRETCH WHITE KBX/ECO"** prints have typical "lamination/plastic" effect with soft feel and much "richer" look, as compared to normal non stretchable white ink / khadi prints.

### Product Feature :

ASPECT : Thick White Paste  
Composition : Ready-made proprietary preparation

### Application & Recipes:

<b>"STRETCH WHITE KBX-ECO"</b>	: 97.0 77 parts
Excellent 500-ECO	: 03.0 03 parts
Laser 5050	: nil 20 parts
	-----
	100.0

Print → Dry → Cure at 140°C for 4 – 5 minutes

**Fusing Machine 160°C For 10 to 15 Sec**  
Screen **120 x 120 For Hand/ Flat Bed Printing**  
**80 x 80 For Rotary Screen Printing**

### Extra Precautions / Check Point :

Use 1 –2 % Glycerin to avoid chocking of screens.  
Fusing of Garments is preferred for better rubbing fastness after curing.  
Note : Kindly keep Open mesh of Rotary Screen for high opacity on dark dyed fabric.

knowledge and experience. In view of the many factors that may affect processing/printing and application of our product, these data do not relieve processors/printers from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product.

Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility.

It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

Electron Group  
230 New Apollo Estate, Mogra Lane, Andheri (E), Mumbai 400069, India. Ph- +91 22 4050 8888  
Fax- +91 22 28269224, e-mail- info@electrongroup.com, website- <http://www.electrongroup.com>

Copyright © 2011 Electron Group