



# Zaritex 1200

**(Self Cross Linking, Acrylic binder for zari printing to be printed alongwith Disperse/Reactive & Khadi)**

It is specially desinged for Zari printing.

It is does not give harsh feeling.

It is does not give watermarks around zari printing.

### PROPERTIES :

- 1. Appearance : Slightly Viscous Milky White Liquid
- 2. NATURE : Aqueous dispersion of thermally crosslinkable polymer
- 3. pH : 4 to 4.5
- 4. Density. : At 20<sup>o</sup>c approx.1.02 g/cm<sup>2</sup>
- 5. Solubility : Miscibile with water in all proportion

### APPLICATIONS

ZARITEX 1200	80%	85%
GLITTER POWDER	15%	10%
UREA	03%	03%
DEFORMER	01%	01%
AMMONIA	01%	01%
	-----	-----
	100%	100%

Screen should used of 40 x 40 or 60 x 60 (threads per sq inch) depending on the particle size of Zari/glitter powder used.

PRINT → DRY → CURE

As ZARITEX 1200 is self crosslinking, no catalyst is required for polymerization of binder. The pH of the print paste should be atleast 7.5 to 8.5, lower pH values must be corrected by addition of liquorammonia to avoid polymerization & hence choking

On polyester nylon & their blends with cotton & viscose, addtion of 2 to 3% Excellent 200(Fixer) is necessary to improve the fastness. Such an addition can also futher

## improve the fastness on cotton to a certain Extent(Particularly wet Fastness).

The information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and are based on our current knowledge and experience. In view of the many factors that may affect processing/printing and application of our product, these data do not relieve processors/printers from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product.

Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility.

It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

Electron Group  
230 New Apollo Estate, Mogra Lane, Andheri (E), Mumbai 400069, India. Ph- +91 99200 77766  
e-mail- [info@electrongroup.com](mailto:info@electrongroup.com), website- <http://www.electrongroup.com>

Copyright © 2025 Electron Group